

Thermal Performance Data

Visions 3500 Double Hung Picture/Transom Windows (9311)
(J-channel)



US Qualification Criteria	Climate Zone	U-Value	SHGC	
<p>As of January 2016</p>	Northern	≤ 0.27	Any	Prescriptive
		$= 0.28$	≥ 0.32	Equivalent Energy Performance
		$= 0.29$	≥ 0.37	
		$= 0.30$	≥ 0.42	
	North-Central	≤ 0.30	≤ 0.40	
	South-Central	≤ 0.30	≤ 0.25	
Southern	≤ 0.40	≤ 0.25		

Canadian Qualification Criteria	Climate Zone	U-Value	or	Energy Rating
<p>As of February 2015</p>	Zone 1	≤ 1.60		≥ 25
	Zone 2	≤ 1.40		≥ 29
	Zone 3	≤ 1.20		≥ 34
	Air Leakage ≤ 0.3 cfm/ft ²			

U-Value

A measurement of how much energy a material conducts. The lower the U-Value, the greater the insulating effect.

Solar Heat Gain Coefficient (SHGC)

Measures how well a window or door prevents heat from passing through it. The lower a window or door's SHGC, the less heat it allows to pass through it.

Visible Light Transmittance

The amount of light in the visible portion of the spectrum that passes through a glazing material.

Condensation Resistance Rating

Measures how well a window resists the formation of condensation on the inside surface. The higher the number the better resistance to condensation.

Energy Rating

A value demonstrating the balance between U-Value, SHGC and air leakage. The higher the number, the more efficient the product.

R-Value

A measurement of how much a material resists heat transfer. A higher R-Value means a greater insulating effect and a lower rate of heat flow out of the home. While **R-value** measures resistance to heat transfer, **U-value** measures the rate of heat transfer. In simple terms, **U-value** is the mathematical reciprocal of **R-value**; that is, $U = 1/R$ and $R = 1/U$.

^a Total Unit calculations are derived from computer simulations that are then verified by 3rd party testing in accordance with NFRC 100, NFRC 200, and NFRC 500.

^b Published values reflect 3mm/3mm glass lite thicknesses.

ENERGY PERFORMANCE DATA														CANADIAN ENERGY PERFORMANCE DATA				
Visions 3500 Double Hung Picture/Transom Windows (9311)														ENERGY STAR				
Grille Option	Glazing thickness	³NFRC Total Unit Calculations ⁴Glazing Option	CPD #	U-Value	Solar Heat Gain Coefficient	Visible Light Transmittance	Condensation Resistance Rating	US ENERGY STAR V 6.0				U-Value (metric)	Maximum Air Leakage L/s/m²	Air Infiltration/Exfiltration Average	Energy Rating	CANADA ENERGY STAR v 4.1		
								N	NC	SC	S					1	2	3
								No GIA or SDL	3/4" Clear Insul	WEA-N-306-00557-00001	0.45					0.67	0.70	45
3/4" Insul Low-E	WEA-N-306-00687-00001	0.30	0.33	0.60	55		Y				1.70	0.6	0.01	22				
3/4" Insul Low E w/Argon	WEA-N-306-00717-00001	0.26	0.33	0.60	59		Y		Y		1.48	0.6	0.01	27	Y			
3/4" Passive Solar	WEA-N-306-00566-00001	0.31	0.59	0.68	56						1.76	0.6	0.01	36	Y	Y	Y	
3/4" Passive Solar w/Argon	WEA-N-306-00628-00001	0.27	0.59	0.68	60		Y				1.53	0.6	0.01	41	Y	Y	Y	
3/4" Passive Solar Extreme	WEA-N-306-00569-00001	0.25	0.53	0.66	43		Y				1.42	0.6	0.01	39	Y	Y	Y	
3/4" Passive Solar Extreme w/Argon	WEA-N-306-00631-00001	0.22	0.53	0.66	47		Y				1.25	0.6	0.01	43	Y	Y	Y	
3/4" Zo-e-shield 5	WEA-N-306-00688-00001	0.30	0.24	0.53	56				Y	Y	1.70	0.6	0.01	17				
3/4" Zo-e-shield 5 w/ Argon	WEA-N-306-00718-00001	0.26	0.24	0.53	59		Y		Y	Y	1.48	0.6	0.01	21	Y			
3/4" Zo-e-shield 5 Extreme	WEA-N-306-00578-00001	0.24	0.23	0.54	44		Y		Y	Y	1.36	0.6	0.01	23	Y	Y		
3/4" Zo-e-shield 5 Extreme w/ Argon	WEA-N-306-00640-00001	0.21	0.23	0.54	48		Y		Y	Y	1.19	0.6	0.01	27	Y	Y	Y	
3/4" Zo-e-shield 6	WEA-N-306-00601-00001	0.30	0.24	0.54	58				Y	Y	1.70	0.6	0.01	17				
3/4" Zo-e-shield 6 w/ Argon	WEA-N-306-00663-00001	0.26	0.23	0.54	61		Y		Y	Y	1.48	0.6	0.01	21	Y			
3/4" Zo-e SafeGuard Certified	WEA-N-306-00607-00001	0.30	0.24	0.54	59				Y	Y	1.70	0.6	0.01	17				
3/4" Zo-e SafeGuard Certified w/ Argon	WEA-N-306-00669-00001	0.26	0.23	0.54	62		Y		Y	Y	1.48	0.6	0.01	21	Y			
1" Zo-e-shield 7	WEA-N-306-00611-00001	0.23	0.22	0.44	67		Y		Y	Y	1.31	0.6	0.01	24	Y	Y		
1" Zo-e-shield 7 w/ Argon	WEA-N-306-00673-00001	0.19	0.22	0.44	71		Y		Y	Y	1.08	0.6	0.01	29	Y	Y	Y	
3/4" Insul Low-E 240	WEA-N-306-00572-00001	0.31	0.22	0.34	56					Y	1.76	0.6	0.01	14				
3/4" Insul Low-E 240 w/Argon	WEA-N-306-00634-00001	0.27	0.22	0.34	60		Y		Y	Y	1.53	0.6	0.01	19	Y			
3/4" Insul Low-E 340	WEA-N-306-00575-00001	0.30	0.16	0.33	57				Y	Y	1.70	0.6	0.01	12				
3/4" Insul Low-E 340 w/Argon	WEA-N-306-00637-00001	0.26	0.16	0.33	61		Y	Y	Y	1.48	0.6	0.01	17	Y				
3/4" Bronze Low E	WEA-N-306-00560-00011	0.30	0.34	0.45	57			Y		1.70	0.6	0.01	22					
3/4" Bronze Low E w/Argon	WEA-N-306-00622-00011	0.26	0.34	0.45	60		Y	Y		1.48	0.6	0.01	27	Y				
Less Than 1" GIA or SDL	3/4" Clear Insul	WEA-N-306-00557-00002	0.45	0.60	0.63	45					2.56	0.6	0.01	19				
	3/4" Insul Low-E	WEA-N-306-00687-00002	0.30	0.30	0.54	55			Y		1.70	0.6	0.01	20				
	3/4" Insul Low E w/Argon	WEA-N-306-00717-00002	0.26	0.30	0.54	59		Y	Y		1.48	0.6	0.01	25	Y			
	3/4" Passive Solar	WEA-N-306-00566-00002	0.31	0.53	0.61	56					1.76	0.6	0.01	32	Y	Y		
	3/4" Passive Solar w/Argon	WEA-N-306-00628-00002	0.27	0.53	0.61	60		Y			1.53	0.6	0.01	37	Y	Y	Y	
	3/4" Passive Solar Extreme	WEA-N-306-00569-00002	0.25	0.48	0.59	43		Y			1.42	0.6	0.01	37	Y	Y	Y	
	3/4" Passive Solar Extreme w/Argon	WEA-N-306-00631-00002	0.22	0.48	0.59	47		Y			1.25	0.6	0.01	40	Y	Y	Y	
	3/4" Zo-e-shield 5	WEA-N-306-00688-00002	0.30	0.22	0.47	56			Y	Y	1.70	0.6	0.01	15				
	3/4" Zo-e-shield 5 w/ Argon	WEA-N-306-00718-00002	0.26	0.22	0.47	59		Y	Y	Y	1.48	0.6	0.01	20	Y			
	3/4" Zo-e-shield 5 Extreme	WEA-N-306-00578-00002	0.24	0.21	0.48	44		Y	Y	Y	1.36	0.6	0.01	22	Y	Y		
	3/4" Zo-e-shield 5 Extreme w/ Argon	WEA-N-306-00640-00002	0.21	0.21	0.48	48		Y	Y	Y	1.19	0.6	0.01	26	Y	Y	Y	
	3/4" Zo-e-shield 6	WEA-N-306-00601-00002	0.30	0.21	0.49	58			Y	Y	1.70	0.6	0.01	15				
	3/4" Zo-e-shield 6 w/ Argon	WEA-N-306-00663-00002	0.26	0.21	0.49	61		Y	Y	Y	1.48	0.6	0.01	20	Y			
	3/4" Zo-e SafeGuard Certified	WEA-N-306-00607-00002	0.30	0.21	0.49	59			Y	Y	1.70	0.6	0.01	15				
	3/4" Zo-e SafeGuard Certified w/ Argon	WEA-N-306-00669-00002	0.26	0.21	0.49	62		Y	Y	Y	1.48	0.6	0.01	20	Y			
	1" Zo-e-shield 7	WEA-N-306-00612-00001	0.23	0.20	0.40	67		Y	Y	Y	1.31	0.6	0.01	23	Y	Y		
	1" Zo-e-shield 7 w/ Argon	WEA-N-306-00674-00001	0.19	0.20	0.40	71		Y	Y	Y	1.08	0.6	0.01	28	Y	Y	Y	
	3/4" Insul Low-E 240	WEA-N-306-00572-00002	0.31	0.20	0.31	56				Y	1.76	0.6	0.01	13				
	3/4" Insul Low-E 240 w/Argon	WEA-N-306-00634-00002	0.27	0.20	0.31	60		Y	Y	Y	1.53	0.6	0.01	18	Y			
	3/4" Insul Low-E 340	WEA-N-306-00575-00002	0.30	0.15	0.30	57			Y	Y	1.70	0.6	0.01	11				
3/4" Insul Low-E 340 w/Argon	WEA-N-306-00637-00002	0.26	0.14	0.30	61		Y	Y	Y	1.48	0.6	0.01	16					
3/4" Bronze Low E	WEA-N-306-00560-00012	0.30	0.31	0.41	57			Y		1.70	0.6	0.01	21					
3/4" Bronze Low E w/Argon	WEA-N-306-00622-00012	0.26	0.31	0.41	60		Y	Y		1.48	0.6	0.01	25	Y				
1" Or Over GIA or SDL	3/4" Clear Insul	WEA-N-306-00557-00003	0.45	0.54	0.56	45					2.56	0.6	0.01	15				
	3/4" Insul Low-E	WEA-N-306-00687-00003	0.30	0.27	0.48	55			Y		1.70	0.6	0.01	18				
	3/4" Insul Low E w/Argon	WEA-N-306-00717-00003	0.26	0.27	0.48	59		Y	Y		1.48	0.6	0.01	23	Y			
	3/4" Passive Solar	WEA-N-306-00566-00003	0.31	0.47	0.54	56					1.76	0.6	0.01	29	Y			
	3/4" Passive Solar w/Argon	WEA-N-306-00628-00003	0.27	0.48	0.54	60		Y			1.53	0.6	0.01	34	Y	Y	Y	
	3/4" Passive Solar Extreme	WEA-N-306-00569-00003	0.25	0.43	0.53	43		Y			1.42	0.6	0.01	34	Y	Y		
	3/4" Passive Solar Extreme w/Argon	WEA-N-306-00631-00003	0.22	0.43	0.53	47		Y			1.25	0.6	0.01	37	Y	Y	Y	
	3/4" Zo-e-shield 5	WEA-N-306-00688-00003	0.30	0.20	0.42	56			Y	Y	1.70	0.6	0.01	14				
	3/4" Zo-e-shield 5 w/ Argon	WEA-N-306-00718-00003	0.26	0.20	0.42	59		Y	Y	Y	1.48	0.6	0.01	19	Y			
	3/4" Zo-e-shield 5 Extreme	WEA-N-306-00578-00003	0.24	0.19	0.43	44		Y	Y	Y	1.36	0.6	0.01	21	Y	Y		
	3/4" Zo-e-shield 5 Extreme w/ Argon	WEA-N-306-00640-00003	0.21	0.19	0.43	48		Y	Y	Y	1.19	0.6	0.01	25	Y	Y	Y	
	3/4" Zo-e-shield 6	WEA-N-306-00601-00003	0.30	0.19	0.43	58			Y	Y	1.70	0.6	0.01	14				
	3/4" Zo-e-shield 6 w/ Argon	WEA-N-306-00663-00003	0.26	0.19	0.43	61		Y	Y	Y	1.48	0.6	0.01	19	Y			
	3/4" Zo-e SafeGuard Certified	WEA-N-306-00607-00003	0.30	0.19	0.43	59			Y	Y	1.70	0.6	0.01	14				
	3/4" Zo-e SafeGuard Certified w/ Argon	WEA-N-306-00669-00003	0.26	0.19	0.43	62		Y	Y	Y	1.48	0.6	0.01	19	Y			
	1" Zo-e-shield 7	WEA-N-306-00612-00002	0.23	0.18	0.35	67		Y	Y	Y	1.31	0.6	0.01	22	Y	Y		
	1" Zo-e-shield 7 w/ Argon	WEA-N-306-00674-00002	0.19	0.18	0.35	71		Y	Y	Y	1.08	0.6	0.01	27	Y	Y	Y	
	3/4" Insul Low-E 240	WEA-N-306-00572-00003	0.31	0.19	0.27	56				Y	1.76	0.6	0.01	12				
	3/4" Insul Low-E 240 w/Argon	WEA-N-306-00634-00003	0.27	0.18	0.27	60		Y	Y	Y	1.53	0.6	0.01	17	Y			
	3/4" Insul Low-E 340	WEA-N-306-00575-00003	0.30	0.13	0.26	57			Y	Y	1.70	0.6	0.01	10				
3/4" Insul Low-E 340 w/Argon	WEA-N-306-00637-00003	0.26	0.13	0.26	61		Y	Y	Y	1.48	0.6	0.01	15					
3/4" Bronze Low E	WEA-N-306-00560-00013	0.30	0.28	0.36	57			Y		1.70	0.6	0.01	19					
3/4" Bronze Low E w/Argon	WEA-N-306-00622-00013	0.26	0.28	0.36	60		Y	Y		1.48	0.6	0.01	24	Y				